

## Neopox® Deco

**Two-component, solvent-based epoxy coating with metallic pigments, for decorative applications**

### Description

Two-component, solvent-based epoxy coating with metallic pigments, suitable for decorative applications

### Fields of application

- Decorative floors and walls of shops, hotels, etc.
- Interior metallic surfaces

*The surfaces require appropriate preparation and priming prior to the application of Neopox® Deco.*

### Properties - Advantages

- Impressive aesthetic result
- Exceptional resistance to abrasion
- High adhesion strength
- Broad service temperature range
- Very good chemical resistance



### Packing

Sets (A+B) of 5kg

### Colours



### Technical Characteristics

Mixing ratio A:B (by weight)	70:30
Density (EN ISO 2811-1)	1,10kg/L (±0,15)
Abrasion resistance (Taber Test, CS 10/1000/1000, ASTM D4060)	57mg
Adhesion strength (EN 1542)	≥2,5N/mm <sup>2</sup>
Resistance to temperatures (dry loading, periodically)	-50°C min. / +140°C max.

**Consumption: 250-330gr/m<sup>2</sup> for two layers (depending on the substrate)**

### Application conditions

Substrate moisture content	<4%
Relative air humidity (RH)	<70%
Application temperature (ambient - substrate)	+12°C min. / +35°C max.

### Curing details

Pot life (RH 50%)	+12°C	2 hours
	+25°C	1 hour
Dry to recoat (RH 50%)	+12°C	36 hours
	+25°C	24 hours
Full hardening	~ 7 days	

*\* Low temperatures and high humidity during application and/or curing prolong the above times, while high temperatures reduce them*

### Appropriate primers on cementitious substrate

	Primer	Description - Details
Solvent-based	<b>Epoxol® Primer</b>	Two-component, solvent-based epoxy primer
Solvent-free	<b>Epoxol® Primer SF</b>	Two-component, solvent-free epoxy primer for flooring applications
	<b>Epoxol® Primer SF-P</b>	Two-component, solvent-free epoxy primer, ideal in cases of substrates with increased porosity
	<b>Neopox® Primer WS</b>	Two-component, solvent-free epoxy primer for wet surfaces (without ponding water or rising moisture)
	<b>Neopox® Primer AY</b>	Two-component, solvent-free anti-osmotic epoxy primer, for floors with rising moisture
Water-based	<b>Acqua Primer</b>	Two-component, water-based epoxy primer

### Appropriate primers on metallic substrate (iron - steel)

Solvent-based	<b>Neopox® Primer 815</b>	Two-component, anticorrosive solvent-based epoxy primers suitable for metallic surfaces
	<b>Neopox® Special Primer 1225</b>	

### Appropriate primers on galvanized substrate - stainless steel

Water-based	<b>Neotex® Inox Primer</b>	One-component, water-based primer, ideal for inox, aluminium, galvanized surfaces
-------------	----------------------------	---

## Instructions for use

### **Substrate preparation**

#### *Concrete*

The concrete must be min. Grade C20/25, with a tensile strength of  $\geq 1,5\text{MPa}$ , and allowed to cure for at least 28 days, taking all the necessary maintenance measures during its curing period. The cementitious substrate must be properly prepared mechanically (e.g. grinding, shot blasting, milling etc.) to smooth out the irregularities, achieve an open-textured surface and ensure optimum adhesion.

The surface must be dry and protected from rising moisture, stable, clean and free of dust, grease, oil, etc. Loose friable material must be fully removed by brushing or sanding with a suitable machine and a high suction vacuum cleaner.

The surface must be as smooth and flat as possible, as well as continuous (ie without voids, cracks etc.)

Repairs to the substrate, filling of joints, blowholes/voids and surface leveling must be carried out using appropriate repairing products, such as the pourable epoxy-cement mortar **Epoxol® CM** and the epoxy putty **Epoxol® Putty**, or/and a mixture of **Epoxol® Primer SF-P** and Quartz Sand M-32 (indicative mixing ratio 1:1-2 w/w), after proper priming.

#### *Metallic surfaces (iron – steel)*

The metallic surfaces must be properly prepared by sandblasting or sanding with a wire brush and should be dry, free of dust, dirt, greasy and oily substances, as well as any poorly adhering coatings. In rusty areas, it is recommended to locally apply the chemical rust converter **Neodur® Metalforce**. New metallic surfaces should be degreased with solvent **Neotex® 1021**.

### **Priming**

For the stabilization of the substrate and sealing of pores, as well as for creating the optimum conditions for stronger adhesion and higher coverage of the subsequent epoxy coating, it is recommended to apply the solvent-based epoxy **Epoxol® Primer** or an alternative appropriate **NEOTEX®** primer (see table), depending on the substrate. In cases of substrates with increased porosity, an additional priming layer may be required.

### **Application**

Once the primer is dry to overcoat, it is recommended to apply the first layer of **Neopox® Deco** diluted 8% w/w with solvent **Neotex® 1021**. The second layer is applied in the same way ~24 hours after the application of the first one (depending also on the atmospheric conditions), diluted 4-8% w/w with solvent **Neotex® 1021**. For any additional layers, **Neopox® Deco** shall be diluted 4% w/w with solvent **Neotex® 1021**. For optimum aesthetic results, it is recommended that the application is done by spray gun.

The two components A & B are mixed in the predetermined ratio (70A : 30B w/w) and, after the addition of the solvent, they are stirred for app. 3-5 minutes with a low speed electric stirrer. It is important to stir thoroughly at the bottom of the container, as well as near the sides, so that the hardener (component B) is evenly distributed.

The mixture is left for a short time period in the container (~1 minute) and then applied. Prior to mixing, mechanical stirring of component A is recommended.

Following the application of **Neopox® Deco**, it is recommended that at least two layers of **Neodur® Varnish** are applied on top, in order to enhance the decorative metallic aesthetic result.

## Special notes

- **Neopox® Deco** should not be applied under wet conditions, or if wet conditions are expected to prevail during the application or the curing period of the product. Increased humidity may have a negative impact on the adhesion, the film properties and/or the final result (e.g. blurry surface, stickiness)
- The components should not have been stored at very low or very high temperatures, especially before mixing. Mixing and stirring of the mixture should be preferably done in the shade. The stirring of the mixture must be done mechanically and not manually with a rod, etc.
- Excessive stirring of the material should be avoided, in order to mitigate the risk of air entrapment. After stirring the mixture, it is recommended to apply the material shortly in order to avoid the development of high temperatures and potential hardening inside the can
- The substrate temperature must be at least 3°C above dew point to reduce the risk of condensation or blooming on the floor finish
- Due to the nature of the material, the direct and constant exposure of the final coating to UV radiation may cause the phenomenon of chalking over time. For this reason, it is not recommended for exposed applications outdoors.
- In case that an extended period of time (>36 hours) has passed between successive layers, it is recommended to lightly sand the surface of the previous layer, in order to avoid possible adhesion problems of the next layer
- Prior to the application on existing epoxy coatings, light sanding of the whole surface is required

---

## Maintenance instructions

- In case of minor spills and stains, it is recommended to remove them as soon as possible by using a soft cloth along with warm clean water (temperature <+60°C)
- For the maintenance cleaning of the surface from dust and dirt, it is recommended to use a vacuum cleaner or a soft bristle broom. The use of hard brushes or wires to remove the stains should be avoided
- For cleaning the surface from hardened stains, it is recommended to use a hard foam mop with a solution of water and ammonia (~3% dilution). Then, rinse off with clean warm water (temperature <+60°C) and dry the surface with a soft towel
- In case of using commercial cleaning products, the use of neutral ones is recommended (pH between 7 and 10). Soaps or all-purpose cleaners containing water-soluble salts or harmful ingredients with high concentration in alkalis or acids should be avoided. Follow the manufacturer's recommendations with respect to the optimum dilution with water. In any case, the first time a commercial cleaning product is used, it is recommended that a trial is made in a small surface area



<b>Appearance (cured)</b>	Glossy
<b>Colours</b>	Blue, green, grey
<b>Packing</b>	Sets (A+B) of 5kg in metal cans
<b>Cleaning of tools – Stains removal</b>	By <b>Neotex® 1021</b> immediately after application. In case of hardened stains, by mechanical means
<b>Volatile organic compounds (V.O.C.)</b>	V.O.C. limit acc. to the E.U. Directive 2004/42/CE for this product of category AjSB “Two-pack reactive performance coatings”: 500g/l (Limit 1.1.2010). V.O.C. content of the ready to use product <500g/l
<b>UFI code</b>	<i>Component A:</i> UF60-7015-V008-FPFX <i>Component B:</i> RJ60-QQK-500S-3120
<b>Storage stability</b>	2 years, stored in its original sealed packing, protected from frost, humidity and exposure to sunlight

The information supplied in this datasheet, concerning the uses and the applications of the product, is based on the experience and knowledge of NEOTEX® SA. It is offered as a service to designers and contractors to help them find potential solutions. However, as a supplier, NEOTEX® SA does not control the actual use of the product and therefore cannot be held responsible for the results of its use. As a result of continual technical evolution, it is up to our clients to check with our technical department that this present data sheet has not been modified by a more recent edition

**HEADQUARTERS - PLANT**  
V. Moira str., Xiropigado  
**LOGISTICS SALES & CENTER**  
Loutsas str., Voro

P.O. Box 2315, GR 19600  
Industrial Area Mandra  
Athens, Greece  
T. +30 210 5557579

**NORTHERN GREECE BRANCH**  
Ionias str., GR 57009  
Kalochori, Thessaloniki, Greece  
T. +30 2310 467275