

# Silimper<sup>®</sup> Nano LM

## Water and oil repellent nano-molecular impregnation compound

### Description

Water and oil repellent, water-based fluorinated nano-molecular impregnation compound, that exhibits high penetrating ability and hydrophobic performance, suitable for exterior and interior construction surfaces

### Fields of application

Vertical (or inclined) mineral porous surfaces such as porous marbles, concrete, cement mortars, plaster, bricks, roof tiles, joint grout, limestone, sandstone, natural stone with continuous surface (i.e. without cracks)

### Properties - Advantages

- Exhibits high penetration due to its nano-molecular structure, protecting from humidity and minimizing the water uptake
- Does not alter the appearance of the surface – no skin formation or yellowing
- Displays early repellence towards water, providing durable hydrophobicity and oleophobicity
- Prevents rain from impregnating the surface and protects it from cracking due to frost
- Facilitates the cleaning of the surface by limiting dirt pick-up & fungal growth
- Presents high resistance to alkalis and prevents efflorescence
- Vapour permeable, allowing the structure to “breathe”
- Does not contain solvents or toxic substances



### Appearance (cured)

Transparent

### Packing

3L and 1L

### Technical characteristics

Density (EN ISO 2811-1)	1,00kg/L (±0,05)
pH	7,5-8,5
Water penetration value (RILEM Test method 11.4, concrete surface)	0ml/min

**Consumption: 100-200ml/m<sup>2</sup> in one layer**  
(depending on the application method and the absorptivity of the substrate)

### Application conditions

Substrate moisture content	<4%
Relative air humidity (RH)	<80%
Application temperature (ambient - substrate)	+5°C min. / +35°C max.

### Curing details

Drying time (+25°C, RH 50%)	2 hours
Dry to recoat (+25°C, RH 50%)	<2 hours
Full hardening (+25°C, RH 50%)	24 hours
<i>* Low temperatures and high humidity during application and/or curing prolong the above times, while high temperatures reduce them</i>	

## Instructions for use

### Substrate preparation

The surfaces must be stable and continuous (without cracks), clean, dry, protected from rising moisture and free of dust, oil, grease, mould and loose materials. Cleaning must be done by mechanical means or by water jetting. It is not recommended to use detergents, as they may affect the material's performance.

### Application

**Silimper® Nano LM** is ready to use. After thorough stirring, **Silimper® Nano LM** is applied onto the dry surface in one layer, by roller, brush or spray, until full impregnation. The application is done starting from the highest parts of the surface and ending at the lowest parts. On highly absorbent substrates, it is recommended to apply an additional layer within 2 hours after applying the previous one. The application surface must remain dry for at least 24 hours after the application.

## Special notes

- **Silimper® Nano LM** should not be applied under wet conditions, or if wet conditions or rainy weather are expected to prevail during the curing period of the product
- If the substrate has been cleaned by water jetting, **Silimper® Nano LM** should be applied after the surface has dried completely (it is recommended to wait for a period of 2-3 days)
- In case of new concrete, **Silimper® Nano LM** must be applied after at least 4 weeks have passed since its laying
- **Silimper® Nano LM** is not resistant to acids
- It should not be applied on surfaces that are subjected to hydrostatic pressures



<b>Appearance</b>	Clear-yellowish liquid
<b>Appearance (cured)</b>	Transparent
<b>Packing</b>	3L and 1L in plastic pails
<b>Cleaning of tools – Stains removal</b>	By water immediately after application. In case of hardened stains, by mechanical means
<b>Volatile organic compounds (V.O.C.)</b>	V.O.C. limit acc. to the E.U. Directive 2004/42/CE for this product of category AhWB: 30g/l (Limit 1.1.2010) - V.O.C. content of the ready-to-use product <30g/l
<b>UFI code</b>	FDD0-40NK-000E-37PD
<b>Versions</b>	<b>Silimper® Nano</b> , silane-siloxane, water-based nano-molecular water-repellent impregnation compound <b>Neotex® Silimper</b> , siloxane-based water repellent of high penetrating ability
<b>Storage stability</b>	18 months, stored in its original sealed packing, protected from frost, humidity and exposure to sunlight

The information supplied in this datasheet, concerning the uses and the applications of the product, is based on the experience and knowledge of NEOTEX® SA. It is offered as a service to designers and contractors to help them find potential solutions. However, as a supplier, NEOTEX® SA does not control the actual use of the product and therefore cannot be held responsible for the results of its use. As a result of continual technical evolution, it is up to our clients to check with our technical department that this present data sheet has not been modified by a more recent edition.

**HEADQUARTERS - PLANT**  
V. Moira str., Xiropigado  
**LOGISTICS SALES & CENTER**  
Loutsas str., Voro

P.O. Box 2315, GR 19600  
Industrial Area Mandra  
Athens, Greece  
T. +30 210 5557579

**NORTHERN GREECE BRANCH**  
Ionias str., GR 57009  
Kalochori, Thessaloniki, Greece  
T. +30 2310 467275

[www.neotex.gr](http://www.neotex.gr) ● [export@neotex.gr](mailto:export@neotex.gr)